

FEATURE	STANDARD	RESULT
Floor type	EN ISO 10582	Heterogeneous SPC
Installation method	-	UNIZIP Click System
Total thickness	EN ISO 24346	6.0 mm
Wear layer thickness	EN ISO 24340	0.55 mm
Size (length and width)	EN ISO 24342	750 x 150 mm
Acoustic underlay	-	Yes (1 mm)
Surface protection	-	UV Full Mat
Embossing of the wear layer	-	Synchronous EIR (Embossed In Register)
Edge bevelling	-	4-sided
Packaging (pieces)	-	16 pcs/pack
Packaging (square metres)	-	1.8 m ² / pack
Weight (g/m ²)	EN ISO 23997	10,250 g/m ²
Dimensional stability	EN ISO 23999	< 0.08 %
Rectangularity and straightness	EN ISO 24342	< 0.1 mm
Flexibility	EN ISO 24344	< 20 mm no cracks
Heat curling	EN ISO 23999	≤ 0.5 mm
Residual indentations	EN ISO 24343-1	0.05 mm
Chair on castors	ISO 4918	resistant (25,000 revolutions)
Anti-slip	DIN 51130 EN 13893 EN 14041: 2004/AC:2006	R10 DS
Abrasion class	EN ISO 10582	Group T
Dynamic friction coefficient	EN 13893:2004	μ = 0.32
Usability class	EN ISO 10874	23/33
Flame retardancy class	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	Bfl-s1
Colour fastness	EN ISO 105-B02	> 6
Chemical resistance	EN ISO 26987	Index 0, excellent
Electrostatic	EN 1815	≤ 2 kV
Electrical resistance	EN 1081	10 ⁹ Ω
Thermal resistance	EN ISO 8302	0.0075 m ² K/W
Thermal conductivity	EN 12667	0.5202 W/mK
Underfloor heating	-	Max 27°C
Formaldehyde emission	EN 14041:2004/AC:2006	E1
Pentachlorophenol content	EN 14041:2004/AC:2006	no DL PCP detected
TVOC after 28 days	ISO 16000	A+
REACH	Regulation (EU) No. 1907/2006	YES



FEATURE	STANDARD	RESULT
Floor type	EN ISO 10582	Heterogeneous LVT
Installation method	-	For gluing
Total thickness	EN ISO 24346	2.5 mm
Wear layer thickness	EN ISO 24340	0.55 mm
Size (length and width)	EN ISO 24342	750 x 150 mm
Acoustic underlay	-	No
Surface protection	-	UV Full Mat
Embossing of the wear layer	-	Synchronous EIR (Embossed In Register)
Edge bevelling	-	4-sided
Packaging (pieces)	-	36 pcs/pack
Packaging (square metres)	-	4.05 m ² / pack
Weight (g/m ²)	EN ISO 23997	4700 g/m ²
Dimensional stability	EN ISO 23999	< 0.1 %
Rectangularity and straightness	EN ISO 24342	< 0.15 mm
Flexibility	EN ISO 24344	< 20 mm no cracks
Heat curling	EN ISO 23999	≤ 0.5 mm
Residual indentations	EN ISO 24343-1	0.05 mm
Chair on castors	ISO 4918	resistant (25,000 revolutions)
Anti-slip	DIN 51130	R10
Abrasion class	EN ISO 10582	Group T
Dynamic friction coefficient	EN 13893:2004	μ = 0.28
Usability class	EN ISO 10874	23/33/42
Flame retardancy class	EN 13501-1	Bfl-s1
	EN ISO 9239-1	
	EN ISO 11925-2	
Colour fastness	EN ISO 105-B02	> 6
Chemical resistance	EN ISO 26987	Index 0, excellent
Electrostatic	EN 1815	≤ 2 kV
Electrical resistance	EN 1081	10 ⁹ Ω
Thermal resistance	EN ISO 8302	0.0166 m ² K/W
Thermal conductivity	EN 12667	0.2841 W/mK
Underfloor heating	-	Max 27°C
Formaldehyde emission	EN 14041:2004/AC:2006	E1
Pentachlorophenol content	EN 14041:2004/AC:2006	not detected DL PCP

